## CGL CCS 6 x 12

**<u>DESCRIPTION</u>** Coconut shell activated carbon with a well developed pore structure,

providing a wide range of molecular adsorption.

**APPLICATIONS** Controls a wide range of molecular weights making it ideally suited

for all general commercial and industrial air filtration applications

requiring chemical filtration.

## **Physical Properties**

Activity for CCL <sub>4</sub> , (ASTM D3467-94)	60 - 65%
Bulk Density, Typical	29 LBS/ CU FT
Moisture content, As Packed	2%
Ball Pan Hardness, (ASTM D3802-79)	98, Minimum
Iodine Number, MG/G (ASTM 4607-94)	1150, Minimum
Ash Content, Maximum	3%

This information has been gathered from standard reference materials and/or test procedures and is believed to be true and accurate. It is offered solely for your consideration and verification. None of the information presented shall be construed as constituting a warranty or representation, expressed, write, or implied, for which we assume legal responsibility or that the information or goods described is fit for any particular use either alone or in combination with other goods or processes, or that its use does not conflict with existing patent rights. No license is granted to infringe on any patent rights or practice any patent inversion.